

KNITTED MESH10
10oz KNITTED MESH
Fire Certificate



TexTesT REPORT # : 1210146
 SAMPLE RECEIVED DATE : 01-20-2009
 TEST STARTED DATE : 01-22-2009
 REPORT ISSUED DATE : 01-22-2009

TEST CONDUCTED: FLAMMABILITY { NFPA 701 TEST METHOD 1 (2004)}

Sample Identification: PRINTNS55FR
 COLOR 1041/A

TEST RESULT:

SAMPLE NUMBER*	CHAR LENGTH (mm)	AFTER FLAME TIME (s)	DRIP BURNS (s)
1	310.0	0.0	0.0
2	240.0	0.0	0.0
3	270.0	0.0	0.0
4	240.0	0.0	0.0
AVG	265.0	0.0	0.0

* Samples were conditioned at least 24 hours at 20±5° before testing

PERFORMANCE CRITERIA FOR TEST: Pass/Fail

REQUIREMENTS	CHAR:	1050 mm Maximum Individual
	DRIP BURN:	2 Seconds Maximum Individual
	AFTER FLAME	2 Seconds Maximum Individual

Note - Conclusion: Based upon the results of the test report, the submitted sample meets the performance requirement as stated in NFPA 701 TEST METHOD 1 (2004).