

# ULTRA Outre

Beyond Your Expectations

## Technical Data Sheet

### PH200SGRA

*8 mil Microporous RC, GRACoL*

PHYSICAL PROPERTIES	RESULT	UNIT	STANDARD
BASIS WEIGHT	200 ± 10	g/m <sup>2</sup>	ISO 536
CALIPER	202 ± 12	um	ISO 534
GLOSS 75 DEGREE	51.0 ± 5.0	%	ISO 8254
ISO BRIGHTNESS	89.0 ± 2.0	%	ISO 2470
OPACITY	94.0 ± 4.0	%	ISO 2471
STIFFNESS (MD)	1.00 ± 0.8	mN.m	ISO 2493
STIFFNESS (CD)	0.55 ± 0.5	mN.m	ISO 2493
<b>NOTE:</b> For use in Epson, Canon, and HP aqueous printers with dye and pigmented inks.	All above information shall only be used as a guide; Buyers shall independently test and determine the products suitability. The mentioned data are an average of test results and should not be used for the purpose of lawsuit or warranty. Above specifications may change without notice.		



[www.myoutre.com](http://www.myoutre.com)

#1 Network  
309 Professional Park Avenue  
Effingham, IL 62401  
Phone: 217-536-5737  
Fax: 217-536-5141

10/12/09