

ULTRA Outre

Beyond Your Expectations

Technical Data Sheet

PH255SGRA

10 mil Microporous RC, GRACoL

PHYSICAL PROPERTIES	RESULT	UNIT	STANDARD
BASIS WEIGHT	255 ± 10	g/m ²	ISO 536
CALIPER	270 ± 12	um	ISO 534
SMOOTHNESS BEKK	500 OVER	sec	ISO 5627
GLOSS 75 DEGREE	54.0 ± 5.0	%	ISO 8254
ISO BRIGHTNESS	90.0 ± 4.0	%	ISO 2470
OPACITY	96.0 ± 4.0	%	ISO 2471
WHITENESS L*	95.5 ± 1.5		
a*	0.0 ± 0.8		ISO 5631
b*	-1.0 ± 0.8		
STIFFNESS (MD)	2.50 ± 1.0	mN.m	ISO 2493
STIFFNESS (CD)	1.40 ± 0.6	mN.m	ISO 2493
NOTE: For use in Epson, Canon, and HP aqueous printers with dye and pigmented inks.	All above information shall only be used as a guide; Buyers shall independently test and determine the products suitability. The mentioned data are an average of test results and should not be used for the purpose of lawsuit or warranty. Above specifications may change without notice.		



www.myoutre.com

#1 Network
309 Professional Park Avenue
Effingham, IL 62401
Phone: 217-536-5737
Fax: 217-536-5141

10/12/09